

Agriculture, Vehicles Parts, Gardening and Lawn

Properties

- Good Processability

Form of Delivery

-  Bags
-  Bulk
-  Big bags

Colours

- Natural
- Black
- Custom Colours



Grades	Density	MFI	Characteristics	Typical Applications
TERmicron® mPE LMD (C6) (1460)	0,936	7,5	Good Mouldability, Good Toughness, High ESCR, High Rigidity, Low Temperature Impact Resistance	Automotive Exterior Parts, General Purpose, Industrial Containers, Agriculture
TERmicron® mPE LMD (C6) (1490)	0,936	12	Good Flow, Good Mouldability, Good Processability, Good Stiffness, Good Toughness	Agricultural, Vehicles Parts, Automotive, General Purpose, Tanks
TERmicron® PE LMD (C6) (1613)	0,938	4,8	Good Impact Resistance, Good Processability, Good Stiffness, Good Toughness	Diesel Fuel Tanks, Automotive, Agriculture, Vehicles Parts
TERmicron® PA 6 01 247 / 10	1	247	Medium Viscosity Polyamide 6 with good Flowability and good Toughness	Tanks, Industrial Products, Agriculture Parts, Lawn & Gardening, General Purpose Moulded Parts, Automotive
TERmicron® PE LLD (C6) 936 08 UV / 05	0,936	8	High ESCR, High Impact Resistance, Low Temperature Impact Resistance, Warp Resistant	Agricultural and Chemical Storage Containers, Technical Parts and Automotive Parts, Design Parts, Lighting Fixtures
TERmicron® PA 6 01 132 / 08	1	132	Medium Viscosity Polyamide 6 with good Flowability	Tanks, Industrial Products, Agriculture Parts, Lawn & Gardening, General Purpose Moulded Parts, Automotive
TERmicron® PE LLD (C6) 935 07 UV / 05	0,935	7	Good Processability, Good Stiffness, Good Toughness, High Flow	Industrial Containers, General Purpose, Tanks, Chemical Tanks, Agriculture Parts
TERmicron® PE LLD 935 09 UV / 05	0,935	9	UV Stabilized, Good Processability	General Purpose Items, Playgrounds, Toys, Industrial Containers, Agriculture Parts
TERmicron® PE LLD 936 04 UV / 05	0,936	4	UV Stabilized, Good Processability	General Purpose Items, Playgrounds, Toys, Tanks, Industrial Containers, Agriculture Parts
TERmicron® PE LLD 936 06 UV / 05	0,936	6	UV Stabilized, Good Processability	General Purpose Items, Playgrounds, Toys, Marine, Agriculture
TERmicron® PE LLD 935 09 UV / 05	0,935	9	UV Stabilized, Good Processability	General Purpose Items, Playgrounds, Toys, Industrial Containers, Agriculture