

Rotomoulding Powders for Tanks

Properties

- Good Quality UV and AO Stabilization

Form of Delivery

-  Bags
-  Bulk
-  Big bags

Colours

- Natural
- Black
- Custom Colours



Grades	Density	MFI	Characteristics	Typical Applications
TERmicron® PE LD 924 01 / 05	0,924	1	High Molecular Weight	General Purpose Items, Industrial Containers, Tanks
TERmicron® PE LD 919 20 / 05	0,919	20	Good Flowability	General Purpose Items, Industrial Containers, Tanks
TERmicron® PE LD 924 02 / 10	0,924	2	High Molecular Weight	General Purpose Items, Industrial Containers, Tanks
TERmicron® PE LD 919 07 / 10	0,919	7	Good Flowability	General Purpose Items, Industrial Containers, Tanks
TERmicron® PE LLD 941 03 UV / 05	0,941	3	UV Stabilized, Good Processability	General Purpose Items, Chemical Tanks, Industrial Containers, Playgrounds, Toys
TERmicron® PE LLD 936 04 UV / 05	0,936	4	UV Stabilized, Good Processability	General Purpose Items, Playgrounds, Toys, Tanks, Industrial Containers, Agriculture
TERmicron® PE HD (C6) (1314)	0,939	3	Good Impact Resistance, Good Stiffness, Good Toughness	Automotive Fuel Tanks, Septic Tanks, Industrial Tanks, Large Tanks
TERmicron® PA 6 01 132 / 08	1	132	Medium Viscosity Polyamide 6 with good Flowability, Good Impact Resistance	Tanks, Automotive & Industrial Products, Agriculture Parts, Lawn & Gardening
TERmicron® PA 6 01 140/ 08	1	140	Medium Viscosity Polyamide 6 with good Flowability, Good Impact Resistance	Tanks, Automotive & Industrial Products, Agriculture Parts, Lawn & Gardening, General Purpose Moulded Parts
TERmicron® PA 6 01 145 / 08	1	145	Medium Viscosity Polyamide 6 with good Flowability, Good Impact Resistance	Tanks, Automotive & Industrial Products, Agriculture Parts, Lawn & Gardening, General Purpose Moulded Parts
TERmicron® PE X-HD (1505)	0,943		Crosslinkable, Good Processability, High ESCR, High Impact Resistance	Fuel Tanks, Industrial Containers
TERmicron® PE LLD (C8) 939 04 UV / 05	0,939	4	Octene Comonomer, UV Stabilized	Tanks, Industrial Items, Marine
TERmicron® PP C 905 15 (4014)	0,905	15	UV Stabilized, High Heat Resistance, Good Impact, High Stiffness	Automotive, Under the Hood, High Temperature Applications, Tanks
TERmicron® mPE LMD (C6) (1460)	0,936	7,5	Good Mouldability, Good Toughness, High ESCR, High Rigidity, Low Temperature Impact Resistance	Automotive Exterior Parts, Tanks, General Purpose, Industrial Containers, Agriculture
TERmicron® mPE LMD (C6) (1490)	0,936	12	Good Flow, Good Mouldability, Good Processability, Good Stiffness, Good Toughness	Agricultural, Vehicles Parts, Automotive, General Purpose, Tanks
TERmicron® PE LMD (C6) (1613)	0,938	4,8	Good Impact Resistance, Good Processability, Good Stiffness, Good Toughness	Diesel Fuel Tanks, Automotive, Agriculture, Vehicles Parts
TERmicron® PE LLD (C6) 935 05 UV / 05	0,935	5	Good Processability, Good Stiffness, Good Toughness	Industrial Containers, Tanks, Marine
TERmicron® PE LLD (C6) 935 07 UV / 05	0,935	7	Good Processability, Good Stiffness, Good Toughness, High Flow	Industrial Containers, General Purpose, Tanks, Chemical Tanks, Agriculture parts
TERmicron® PE LLD (C6) 936 12 UV / 05	0,936	12	Good Flow, Good Moldability, Good Processability, Good Stiffness, Good Toughness	Containers, Tanks, General Purpose